


SiSiB[®] PC1800

Diethylaminomethyltriethoxysilane

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PC1800 is a novel alfa silane. The close proximity of the nitrogen atom to the silicon atom can accelerate hydrolysis reaction compared to (amino-propyl)silanes.

TYPICAL PHYSICAL PROPERTIES

CAS No.	15180-47-9
EINECS No.	N.A.
Formula	C ₁₁ H ₂₇ NO ₃ Si
Molecular Weight	249.22
Boiling Point	110-130°C [5mmHg] 237°C [760 mmHg]
Flash Point	>110°C
Color and Appearance	Colorless to yellowish clear liquid
Density _{25/25°C}	0.916-0.933
Refractive Index	1.432 [25°C]
Min Purity	98.0% (Grade A) 92.0% (Grade B)

Solubility: SiSiB[®] PC1800 is soluble in most organic solvent like alcohol, acetone, toluene, acetic ether and gasoline; also soluble in water;

APPLICATIONS

SiSiB[®] PC1800 can be used as crosslinking agent for RTV silicone rubber.

SiSiB[®] PC1800 can be used as anchoring agent of synthetic resin;

SiSiB[®] PC1800 can be used as raw material of finishing agent to manufacture fabrics.

SiSiB[®] PC1800

Diethylaminomethyltriethoxysilane

PACKING AND STORAGE

SiSiB[®] PC1800 is supplied in 20Kg plastic drum, 180Kg steel drum or 900Kg IBC container.

In the unopened original container SiSiB[®] PC1800 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.