



INTRODUCTION

SiSiB® HR6820 is low hardness products for molding.

KEY FEATURES

Very low hardness.

Rohs test passed.

TYPICAL PHYSICAL PROPERTIES

Product	SiSiB® HR6820 HCE
Appearance	Translucent
Curing Agent	C-8
Curing Agent Content	2.0%
Curing Condition	170°C×5min
Hardness (Shore A)	20+/-2
Tensile Strength (MPa)	Min. 3.5
Elongation (%)	Min. 750
Tensile Set (%)	Max.8.0
Tear Strength (KN/m)	Min. 8.0

APPLICATIONS

Parts

Swimming caps

PACKING AND STORAGE

SiSiB® HR6820 is supplied in 20Kg box, with plastic bag inside.

Store in a cool and dry place out of direct sunlight.

NOTES

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] HR6820 HCE

- 2 -

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia